Inteplast Group
World-Pak Division
IntePlus® Business Dept.

TECHNICAL DATA SHEET

IntePlus®

Film Type: XF - RV

Property	Test Method	Unit	Film Direction	Typical Value	
Thickness	XFWI0201	GSM	--	150 ± 10%	170 ± 10%
		Mil	--	5.7 ± 10%	7.2 ± 10%
Tensile	ASTM-D882	lb/in	MD	35	42
@ Ultimate			TD	28	30
Elongation	ASTM-D882	%	MD	650	650
@ Ultimate			TD	450	500
Dart Impact	ASTM-D1709 (Method A)	grams	--	950	1,200
PP Tear	ASTM-D2582	grams	MD	10,000	11,000
			TD	10,000	11,000
Beach	ASTM-D781	in-lb	MD	> 42	> 42
Puncture			TD	> 42	> 42
MVTR	ASTM E96 (Method B)	US Perm	--	0.067	0.059
Fire Rating	ASTM E84	Class	--	A	A

Please note that the above information is to the best of our knowledge and is made without guarantee. These are typical property values and are intended as guides only, not as specification limits. We can not anticipate all conditions under which this information and our products, or products of other manufacturers in combination with our products may be used. Users are advised to conduct their own test and evaluation to determine the safety and suitability for their own purposes. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products.

For additional information, call 1-800-452-2117, extension 8058.

Issued Date: 12/17/07